

Technical Data/ Product Specifications

3 Safety-Walk™ Wet Area Matting 3200

(Also known as 3M™ Entrap Wet Area Matting)

1.0 Product Description

The product is a durable, oil-resistant, all-vinyl floor mat having an open, continuously patterned surface. Its open construction allows liquids to run easily through the mat. The product provides a slip-resistant, comfortable walking surface for barefoot traffic and requires only simple maintenance.

2.0 Intended Use

For use in wet areas to provide a slip-resistant, comfortable walking surface for barefeet.

3.0 Standard Sizes

Pre-Cut Mats: 3 ft. x 10 ft.

Rolls: 3 ft. x 20 ft.

Custom Lengths:

Width: 3 feet

Length: 2 feet to 30 feet in 1 foot increments.

4.0 Color

Wheat, Horizon Blue

5.0 Requirements

General Requirements

The product shall be made of oil-resistant, vinyl, nonwoven continuous filaments bonded together to form a durable, resilient mat.

Detailed Requirements:

Weight (minimum)

ASTM D418-68

6.25 lbs./yd.² (3.4 kg/m²)

Width

(minimum)

35.8 inches (0.91 m)

Thickness (minimum) [1]

ASTM D418-68

0.2 inches (5.0 mm)

Contáctanos

www.tecip.com.pe



Escribenos o llámanos

986-650-380 | 981-175-599 | 942-780-265



@tecip.com.pe



TECNOLOGÍA INDUSTRIAL PERUANA S.A.C.

5.0 Requirements (continued)

Flammability	
DOC-FF-1-70 (Pill Test)	Passes
ASTM E-648 Flooring	
Radiant Panel Test	>1.0 watts/cm ² (no ignition)
Electrical Properties	
AATCC-134	0.9 kV [2]
Static Propensity	
Extended Use Temperature	-20°F to 140°F (-29°C to 60°C)
Coefficient of Friction	
ASTM D-1894 [3]	
Dry Leather	1.2
Dry Rubber	1.1
Wet Leather	1.2
Wet Rubber	1.1
Oiled Leather	1.1
Oiled Rubber	1.0
Chemical Resistance[4]	
Degreaser Solutions	Excellent [5]
(non-chlorinated)	Excellent
Dishwashing Soap	Excellent
Isopropyl Alcohol	Poor
Oil, Peanut	Excellent
Oil, Vegetable	Excellent
Soap Solution (1% Tide)	Excellent
Sodium Hydroxide	Excellent
Tri-Sodium Phosphate	Excellent
Water	Excellent
Water (10% Salt)	Excellent
Water (0.2% Chlorinated)	Excellent

- [1] Product may be compressed in package. Thickness is recovered loft.
- [2] Annoyance threshold is considered to be greater than 2.5 kV
- [3] Standard test method static and kinetic coefficients of friction of plastic film and sheeting.
- [4] Complete immersion for 30 days at 72°F (22.2° C)
- [5] Excellent – less than 3% dimension change and less than 5% hardness change
Poor – more than 3% dimension change and more than 5% hardness change. Product not recommended for use in presence of the chemical.

6.0 Packaging and Marking

Packaging: One per carton.

Marking: Each carton shall be marked with product name, size, color, and manufacturer's trade name.

7.0 Cleaning

Routine Maintenance:

Contáctanos

www.tecip.com.pe



Escribenos o llámanos

986-650-380 | 981-175-599 | 942-780-265



@tecip.com.pe



7.0 Cleaning (continued)

3. If needed, mop or flush service area.
4. If needed, flush both sides of the mat with warm water to remove remaining dirt.
5. Allow mat to dry flat before placing mat back into service.

For Wet Areas:

Flush both sides of mat daily with warm water.

Periodic Maintenance:

1. Remove mat from service area if needed (no drainage in area).
2. Mop mat(s) on both sides with a disinfectant cleaner and let stand for ten (10) minutes.
3. Flush mat with warm water.
4. Allow mat to dry flat before placing back into service

8.0 Weight and Cube per Case

Size	Approximate Weight	Cube
3 ft. x 10 ft.	25 lb.	2.000 cu. ft.
3 ft. x 20 ft.	49 lb.	2.496 cu. ft.

Contáctanos

www.tecip.com.pe



Escribenos o llámanos

986-650-380 | 981-175-599 | 942-780-265



@tecip.com.pe



3M Branch Sales Offices

ANCHORAGE

11151 Calaska Circle
Anchorage, AK 99515
Telephone: 907/522-5200
Facsimile: 907/522-1645

CONTINENTAL UNITED STATES

Customer Service Department
3M Center Building 223-5N-07
St. Paul, MN 55144-1000
Order Entry 1-800-852-9722
Facsimile: 1-800-447-0408

HONOLULU

4443 Malaai Street
Honolulu, HI 96818
Mail to: P.O. Box 30048
Honolulu, HI 96820
Telephone: 808/422-2721
Facsimile: 808/422-9557

3M CANADA

1840 Oxford Street East
London, Ontario, Canada
N5V 3G2
Mail to: P.O. Box 5757
London, Ontario, Canada
N6A 4T1
Telephone: 800/364-3577
Facsimile: 800/479-4453

Important Notice:

This flyer is intended to be an introductory summary. The information provided is based upon typical conditions and is believed to be reliable; however, due to the wide variety of intervening factors 3M does not warrant that the results will necessarily be obtained. All details concerning product specifications and terms of sale are available from 3M.

Contáctanos

www.tecip.com.pe



Escribenos o llámanos

986-650-380 | 981-175-599 | 942-780-265



@tecip.com.pe

